

FIBERLAM RR15



| Product | Product category | Lamination |
|--|------------------|------------------------------|
| PTFE CAST FILM LAMINATED GLASS FABRIC | FIBERLAM SERIE | MULTILAYER PTFE CAST FILM |

| Properties | Metric | | Imperial | |
|---|------------|-------------------|-------------|------------|
| Standard width(s) <i>Please ask for other widths</i> | 1000 | mm | 39.5 | inches |
| Thickness | 0,17 | mm | 0.0067 | inches |
| Weight | 340 | gr/m ² | 10.03 | oz/sq yd |
| PTFE content | 69 | % | 69 | % |
| Tear resistance (<i>Trapez</i>) | 125 | N | 28 | Ibs |
| Tensile strength | 1400 | N/5 cm | 160 | Ibs/inches |
| Temperature resistance | -73 to 260 | °C | -100 to 500 | °F |

Colour : Red / Red

FIBERLAM laminated products features multi-layer PTFE cast film laminated on both sides of PTFE / glass fabric, uniform thickness, crack and pinhole free surface. Outperforms traditional PTFE-coated materials; long-lasting release properties make cleaning easier; low wicking properties extend useful life. Lamination eliminates the possibility of thin spots found in traditional PTFE coated materials, which often lead to their premature failure.

FDA Compliant

Suitable for use in direct food contact applications under the applicable requirements of, 21CFR 177.1550

Applications

Platen covers for PVC window framers welding.

The product does not contain banned substances as described in RoHS directive and will not affect RoHS compliance.



Note: Nominal thickness, weight and tensile strength values are typical and are not intended as a specification minimum. Weight Tolerance g/m² = ±%5
 All technical data are based on average values. These values are not intended for use in preparing specifications. Technical information contained herein are based on test results FIBERFLON believes to be reliable, but they are not to be construed in any manner as warranties expressed.
 All data is subject to change without notice.